

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11

Publication number:

0 060 601
A1

12

EUROPEAN PATENT APPLICATION

21

Application number: 82200309.1

51

Int. Cl. 3: C 08 L 67/02, C 08 L 51/00

22

Date of filing: 09.03.82

30

Priority: 09.03.81 US 241876

71

Applicant: STAUFFER CHEMICAL COMPANY, Westport
Connecticut 06880 (US)

43

Date of publication of application: 22.09.82
Bulletin 82/38

72

Inventor: Silberberg, Joseph, 1084 East 28th Street,
Brooklyn, NY 11210 (US)

84

Designated Contracting States: BE DE FR IT NL

74

Representative: Urbanus, Henricus Maria, Ir. et al, c/o
Vereenigde Octrooibureaux Nieuwe Parklaan 107,
NL-2587 BP 's-Gravenhage (NL)

54 Blends of a polyester resin and impact resistant Interpolymer.

57 Blends of a polyester resin, such as polyethylene or polybutylene terephthalate, and an impact resistant Interpolymer comprising crosslinked acrylic or methacrylic rubber, crosslinked styrene-acrylonitrile, and uncrosslinked styrene-acrylonitrile polymer components are disclosed.

EP 0 060 601 A1

ACTORUM AG

BEST AVAILABLE COPY

BLENDS OF A POLYESTER RESIN
AND IMPACT RESISTANT INTERPOLYMER

Background of the Invention

Field of the Invention

5 The present invention relates to blends of a polyester resin, such as polybutylene or polyethylene terephthalate, and an impact resistant interpolymer. The resulting blends find utility as a raw material in the fabrication of formed parts.

10 Description of the Prior Art

Thermoplastic polyester resins which are based on the reaction of aliphatic or aromatic dicarboxylic acids and aliphatic or cycloaliphatic diols are tough materials which find principal utility as an injection molding material for the formation of molded parts having good resistance to friction and wear. Various attempts have been made to improve the impact resistance of such materials. For example, in U.S. Patent No. 3,919,353 to L. Castelnovo et al. it is suggested that the polyester resin be blended with a crosslinked polymer having a second order transition temperature lower than 0°C. which is grafted with or which contains polar and/or polarizable monomers or groups. Examples of such polymers are polybutadiene, butadiene-styrene copolymers, butadiene-acrylonitrile copolymers, ethylene-propylene rubbers, polyisobutene, and polyisoprene. Examples of polar grafting monomers or polarizable groups include the acrylic and methacrylic esters,

15
20
25

vinyl acetate, acrylonitrile, styrene, and the alkyl styrenes.

Various acrylate based multistage interpolymers which differ from the impact resistance additive proposed by Castelnuovo et al. are known. For example, U.S. Patent No. 3,655,826 to R. P. Fellmann et al. proposes a three-stage interpolymer which is useful as an impact resistance improver for a variety of thermoplastic polymers without naming thermoplastic polyester resins as an example of a suitable substrate resin. Another three-stage interpolymer comprising acrylate, styrene, and acrylonitrile moieties is described in U.S. Patent No. 3,944,631 to A. J. Yu et al. This interpolymer has been described in the prior art as an impact improvement additive for polycarbonate resins (U.S. Patent No. 4,148,842), for blends of chlorinated vinyl chloride and vinyl chloride polymers (U.S. Patent No. 4,160,793), and for vinyl chloride polymers (U.S. Patent No. 4,168,285).

Summary of the Present Invention

The present invention relates to blends of: (1) a thermoplastic polyester resin, such as polybutylene or polyethylene terephthalate; and (2) an impact resistant interpolymer comprising crosslinked (meth)acrylate, crosslinked styrene-acrylonitrile and uncrosslinked styrene-acrylonitrile polymer components. The interpolymer composition is described in U.S. Patent No. 3,944,631 to A. J. Yu et al. When the amount of polyester resin predominates in the blend, the interpolymer acts as an impact modifier and processing

aid for the normally tough, but relatively impact sensitive polyester resin. At relatively high levels of the interpolymer, the polyester resin functions as a modifier to increase the strength and modulus of the blend as compared to presence of the interpolymer alone, while retaining good heat distortion temperature, elongation, and impact resistance characteristics.

Description of Preferred Embodiments

10

The blends of the present invention comprise: (1) a polyester resin; and (2) an impact resistant interpolymer comprising crosslinked (meth)acrylate, crosslinked styrene-acrylonitrile, and uncrosslinked styrene-acrylonitrile polymeric components.

15

The term "polyester" resin, as used herein, is intended to encompass those thermoplastic polyester resins which are made by the condensation polymerization of aliphatic or aromatic dicarboxylic acids and aliphatic or cycloaliphatic diols. Such materials are well known and are described in the literature at a number of places including Modern Plastics Encyclopedia, 1977-78, pp. 56, 61 and 62 and Handbook of Plastics and Elastomers, C. A. Harper, ed., McGraw-Hill, Inc., 1975, pp. 1-87 to 88. Representative polymers of this type include polyethylene and polybutylene terephthalate. Commercially available resins of this type include those sold under the following trademarks: VALOX (General Electric); CELANEX (Celanese); and GAFITE (GAF Corp.). The polyester resin that is selected for use in the present invention can contain any of the additives conventionally used in such resins including fillers (e.g., glass,

20

25

30

talc, mica, clay, calcium carbonate, wollastonite, carbon fibers, mineral fibers, etc.), impact modifiers, antioxidants, etc.

The terminology "impact resistant interpolymer
5 comprising crosslinked (meth)acrylate, crosslinked
styrene-acrylonitrile, and uncrosslinked styrene-
acrylonitrile components" is meant to encompass the
type of interpolymer compositions described in U.S.
Patent No. 3,944,631 to A. J. Yu et al. These inter-
10 polymer compositions are formed by the following type
of three-step, sequential polymerization process:

1. emulsion polymerizing a monomer charge (here-
in designated "(meth)acrylate", for the purposes of
the present invention), of at least one monomer
15 selected from the C_2 - C_{10} alkyl acrylates, C_8 - C_{22} alkyl
methacrylates or compatible mixtures thereof, in an
aqueous polymerization medium in the presence of an
effective amount of a suitable di- or polyethylenically
unsaturated crosslinking agent for such a type of mon-
20 omer, with the C_4 - C_8 alkyl acrylates being the pre-
ferred (meth)acrylate monomers for use in this step;
2. emulsion polymerizing a monomer charge of
styrene and acrylonitrile in an aqueous polymerization
medium, also in the presence of an effective amount of
25 a suitable di- or polyethylenically unsaturated cross-
linking agent for such monomers, said polymerization
being carried out in the presence of the product from
Step 1 so that the crosslinked (meth)acrylate and cross-
linked styrene-acrylonitrile components form an inter-
30 polymer wherein the respective phases surround and
penetrate one another; and

3. either emulsion or suspension polymerizing a

monomer charge of styrene and acrylonitrile, in the absence of a crosslinking agent, in the presence of the product resulting from Step 2. If desired, Steps 1 and 2 can be reversed in the above-described procedure.

5 This product, which is used as the impact resistant interpolymer component in the blends of the present invention generally comprises from about 5% to about 50%, by weight, of the above-identified cross-linked (meth)acrylate component, from about 5% to about
10 35%, by weight, of the crosslinked styrene-acrylonitrile component and from about 15% to about 90%, by weight, of the uncrosslinked styrene-acrylonitrile component. It contains little graft polymerization between the
15 crosslinked (meth)acrylate polymeric component. Further details regarding this type of polymer composition can be found in U.S. Patent No. 3,944,631 to A. J. Yu et al., which is incorporated herein by reference.

20 The blends of the present invention can be formulated in weight ratios of polyester resin to interpolymer resin of from about 10:90 to about 90:10 depending upon the precise physical properties desired in the end product. Generally, blends containing amounts of polyester and interpolymer in the range of from about
25 30:70 to about 70:30 are less desired since the blend tends to lose some of the respective desired characteristics of either of its constituents. Therefore, blends of from 10:90 to 30:70 and 70:30 to 90:10 are most desired.

30 Blending can be achieved by any of the well-known polymer blending techniques, such as a two-roll or Banbury mixing, single or multiple screw extrusion,

0060601

- 6 -

or any other method which applies sufficient heat
(e.g., 200° to 275°C., preferably 225°C. to 250°C.)
and shear to the respective polymeric ingredients
(polyester resin and interpolymer additive) to obtain
5 a satisfactory blend in accordance with the present
invention.

The present invention is further illustrated by
the Examples which follow.

EXAMPLES 1-9

These examples illustrate the fabrication of a number of blends in accordance with the present invention and illustrate various of their physical property characteristics.

A series of blends of polyester resin (VALOX 310 brand from General Electric) and the type of interpolymer described in U.S. Patent No. 3,944,631 to A.J. Yu et al. were prepared along with two control compositions. The interpolymer contained 32%, by weight, crosslinked polybutyl acrylate, 10% by weight, of crosslinked styrene-acrylonitrile (73:27 weight ratio), and 58%, by weight, of uncrosslinked styrene-acrylonitrile (73:27 weight ratio). It was obtained from Stauffer Chemical Company (SCC-1004 brand).

The selected ingredient (in the case of each Control run) or ingredients were first oven dried at 110°C. for 2 hours. The samples that were selected for fabrication were as follows with the amounts being the weight proportions of the selected ingredient(s):

EXAMPLES 1-9 (cont'd.)

	<u>Example</u>	<u>Polyester</u> <u>(VALOX 310 brand)</u>	<u>(SCC-1004 brand)</u>
5	1 (Control)	0	100
	2	10	90
	3	25	75
	4	40	60
	5	50	50
10	6	60	40
	7	75	25
	8	90	10
	9 (Control)	100	0

15 The ingredients were extrusion compounded at about
220°C. in an extrusion apparatus having a 2.5 cm.
barrel diameter, a 20/1 length to diameter ratio, with
a 3:1 compression ratio standard taper screw turning
at 50 rpm through a strand die. The extruded samples
20 were dried overnight at 90°C. prior to being injection
molded to form test plaques. The injection molding
was performed on an injection molding machine from Boy
Company.

 Listed below are the extrusion and injection mold-
ing conditions noted for each sample:

EXAMPLES 1-9 (cont'd.)

<u>Extrusion Conditions</u>		
	<u>Barrel Temp. Range</u>	<u>Die Temp.</u>
5	<u>Example No.</u>	<u>(°C.)</u>
	1	217-220
	2	215-232
	3	215-235
10	4	225-255
	5	225-255
	6	225-255
	7	225-255
	8	225-255
15	9	225-255
		200
		220
		222
		230
		230
		218
		225
		225
		220

In the injection molding operation the barrel temperature for all samples was 210°C. except for the sample for Example 9 which was 250°C. The nozzle heater was set at approximately 50% time on. The injection pressure setting was adjusted for each sample to give proper mold fill.

The following physical properties were noted for each specimen:

EXAMPLES 1-9 (cont'd.)

	<u>Example No.</u>	<u>Tensile Str. (1) (MPa)</u>	<u>Elongation at Break (1) (%)</u>	<u>Flexural Str. (2) (MPa)</u>
5	1	33.3	123	51.3
	2	34.0	141	54.8
	3	37.0	144	59.9
	4	40.6	43	65.4
	5	42.5	53	68.1
10	6	46.1	168	77.1
	7	49.9	237	80.5
	8	53.7	392	90.8
	9	56.0	444	94.2

- 15 (1) ASTM D-638 with the following modifications:
specimens were 0.32 cm. x 0.32 cm. in cross-
section with a gauge length of 1.42 cm.
(2) ASTM D-790, Method I, Procedure B.

	<u>Example No.</u>	<u>Flex Modulus (2) (GPa)</u>	<u>Izod Impact (3) (J/m)</u>	<u>Tensile Impact (4) (KJ/m²)</u>
20	1	1.66	641	421
	2	1.69	566	498
	3	1.78	150	452
25	4	1.88	112	393
	5	1.97	91	320
	6	2.12	85	305
	7	2.25	75	305
	8	2.40	69	284
30	9	2.51	43	301

- (2) ASTM D-790, Method I, Procedure B.
(3) ASTM D-256, Method A, using a 0.32 cm. thick
specimen.
(4) ASTM D-1822, Specimen Type L.

0060601

- 11 -

EXAMPLES 1-9 (cont'd.)

	<u>Example No.</u>	<u>Heat Deflection (5) Temp. (°C.)</u>	<u>Melt Viscosity (6) (poise)</u>
5	1	75.5	3200
	2	77	2900
	3	75.5	--
	4	72	2500
	5	70	--
10	6	77	2600
	7	70	--
	8	56	3200
	9	53	3800

- 15 (5) ASTM D-648 measured at 1.82 MPa on specimen.
(6) measured at 1000 sec.⁻¹ and 230°C. in a capillary rheometer attachment on an INSTRON stress/strain testing machine.

The foregoing Examples set forth certain embodiments of the present invention but should not be construed in a limiting manner. The scope of protection for the present invention is set forth in the claims
5 which follow.

CLAIMS

1. A blend comprising: (1) a polyester resin;
and (2) an impact resistant interpolymer comprising
crosslinked (meth)acrylate, crosslinked styrene-
5 acrylonitrile, and uncrosslinked styrene-acrylonitrile
polymeric components.
2. A blend as claimed in Claim 1 wherein the
interpolymer comprises from about 5% to about 50%, by
weight, of the (meth)acrylate component, from about
10 5% to about 35%, by weight, of the crosslinked styrene-
acrylonitrile component, and from about 15% to about
90%, by weight, of the uncrosslinked styrene-acrylo-
nitrile component.
3. A blend as claimed in Claim 1 or 2 which com-
15 prises a weight ratio of polyester resin to interpoly-
mer of from about 10:90 to about 90:10.
4. A blend as claimed in either Claim 1 or 2
wherein the weight ratio of polyester resin to inter-
polymer is either from about 10:90 to about 30:70 or
20 from about 70:30 to about 90:10.
5. A blend as claimed in either Claim 1 or 2
wherein the (meth)acrylate component of the interpoly-
mer is selected from the group consisting of the cross-
linked C₂-C₁₀ alkyl acrylates, the crosslinked C₈-C₂₂
25 alkyl methacrylates, and compatible mixtures thereof.
6. A blend as claimed in either Claim 1 or 2
wherein the (meth)acrylate component of the interpoly-
mer is a crosslinked C₄-C₈ alkyl acrylate.
7. A blend as claimed in either Claim 1 or 2
30 wherein the polyester resin is polyethylene tere-
phthalate.
8. A blend as claimed in either Claim 1 or 2
wherein the polyester resin is polybutylene terephthal-
ate.

9. A blend as claimed in either Claim 1 or 2 wherein the weight ratio of polyester resin to interpolymer is from about 10:90 to about 90:10 and the interpolymer comprises from about 5% to about 50%,
5 by weight, of a crosslinked polybutyl acrylate component, from about 5% to about 35%, by weight, of the crosslinked styrene-acrylonitrile component, and from about 15% to about 90%, by weight, of the uncrosslinked styrene-acrylonitrile component.



European Patent
Office

EUROPEAN SEARCH REPORT

0060601
Application number

EP 82 20 0309

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 7)
D, A	EP-A-0 006 291 (STAUFFER) *Claims 1-7* -----	1, 2, 5, 6	C 08 L 67/02 C 08 L 51/00
			TECHNICAL FIELDS SEARCHED (Int. Cl. 7)
			C 08 L 67/02 C 08 L 51/00
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15-06-1982	Examiner DECOCKER L.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.